

Test Report	Report No.:	210719212GZU-003	Date: Aug 11, 2021
Applicant:	AILUN ELECTRONIC TECHNOLOGY (H.K) LIMITED		
	Room 01, 21/F Prosper Commercial Building 9 Yin Chong Street, Kowloom, H.K		
Sample Descrip	tion:		

The following submitted sample(s) said to be:

Salu	
:	Monolithic capacitor(Radial), Monolithic capacitor(Axial)
:	NA
:	Jul 21, 2021
:	Jul 21, 2021 to Aug 6, 2021
	:

Tests conducted:

As requested by the applicant, refer to following page(s) for details.

Conclusion:

Tested Sample	Standard	Result
Tested components of submitted sample	Restriction of the use of certain hazardous substance in electrical and electronic equipment (RoHS Directive 2011/65/EU and (EU) 2015/863)	Pass

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch: Prepared by:

Leo Yao



Leo Yao Engineer Michael Pang

Reviewed by:

Assistant Technical Supervisor





<u>Test Report</u>

Report No.: 210719212GZU-003

Date: Aug 11, 2021

Tests conducted:

RoHS Chemical Test

(A) Test Result Summary:

Test Item	Result (mg/kg)			
iest item	(1)	(2)	(3)	(4)
Cadmium (Cd) Content	ND	ND	ND	ND
Lead (Pb) Content	ND	ND	ND	ND
Mercury (Hg) Content	ND	ND	ND	ND
Chromium (VI)(Cr ⁶⁺) Content	ND		ND	
Chromium (VI)(Cr ⁶⁺) Result (By Boiling Water Extraction on Metal) (µg/cm ²)		Negative		Negative
Sum of Polybrominated Biphenyls (PBBs)	ND	ND	ND	ND
Monobromobiphenyl (MonoBB)	ND	ND	ND	ND
Dibromobiphenyl (DiBB)	ND	ND	ND	ND
Tribromobiphenyl (TriBB)	ND	ND	ND	ND
Tetrabromobiphenyl (TetraBB)	ND	ND	ND	ND
Pentabromobiphenyl (PentaBB)	ND	ND	ND	ND
Hexabromobiphenyl (HexaBB)	ND	ND	ND	ND
Heptabromobiphenyl (HeptaBB)	ND	ND	ND	ND
Octabromobiphenyl (OctaBB)	ND	ND	ND	ND
Nonabromobiphenyl (NonaBB)	ND	ND	ND	ND
Decabromobiphenyl (DecaBB)	ND	ND	ND	ND
Sum of Polybrominated Diphenyl Ethers (PBDEs)	ND	ND	ND	ND
Monobromodiphenyl Ether (MonoBDE)	ND	ND	ND	ND
Dibromodiphenyl Ether (DiBDE)	ND	ND	ND	ND
Tribromodiphenyl Ether (TriBDE)	ND	ND	ND	ND
Tetrabromodiphenyl Ether (TetraBDE)	ND	ND	ND	ND
Pentabromodiphenyl Ether (PentaBDE)	ND	ND	ND	ND
Hexabromodiphenyl Ether (HexaBDE)	ND	ND	ND	ND
Heptabromodiphenyl Ether (HeptaBDE)	ND	ND	ND	ND
Octabromodiphenyl Ether (OctaBDE)	ND	ND	ND	ND
Nonabromodiphenyl Ether (NonaBDE)	ND	ND	ND	ND
Decabromodiphenyl Ether (DecaBDE)	ND	ND	ND	ND
Phthalates				
Bis(2-ethylhexyl) phthalate (DEHP)	ND	ND	ND	ND
Butyl benzyl phthalate (BBP)	ND	ND	ND	ND
Dibutyl phthalate (DBP)	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	ND	ND	ND	ND

Page 2 of 9



Report No.: 210719212GZU-003

Date: Aug 11, 2021

Tested samples:

- (1) Dark yellow body (3-1)
- (2) Silver color metal (3-2)
- (3) Dark yellow body (3-3)
- (4) Silver color metal (3-4)

ND = Not detected

mg/kg = milligram per kilogram

Negative = The Cr (VI) concentration is less than 0.10 μ g/cm². The sample is negative for Cr (VI).

(B) RoHS Requirement:

Restricted Substances	Limits
Cadmium (Cd)	0.01% (100 mg/kg)
Lead (Pb)	0.1% (1000 mg/kg)
Mercury (Hg)	0.1% (1000 mg/kg)
Chromium (VI) (Cr ⁶⁺)	0.1% (1000 mg/kg)
Polybrominated Biphenyls (PBBs)	0.1% (1000 mg/kg)
Polybrominated Diphenyl Ethers (PBDEs)	0.1% (1000 mg/kg)
Phthalates (DEHP, BBP, DBP, DIBP)	0.1% (1000 mg/kg)

The above limits were quoted from 2011/65/EU and (EU) 2015/863 for homogeneous material.

(C) Test Method:

Test Item	Test Method	Detection Limit
Cadmium (Cd) Content	With reference to IEC 62321-5 Edition 1.0: 2013, by acid digestion and determined by ICP - OES	2 mg/kg
Lead (Pb) Content	With reference to IEC 62321-5 Edition 1.0: 2013, by acid digestion and determined by ICP - OES	2 mg/kg
Mercury (Hg) Content	With reference to IEC 62321-4 Edition 1.1: 2017, by acid digestion and determined by ICP - OES	2 mg/kg
Chromium (VI)(Cr ⁶⁺) Content	With reference to IEC 62321-7-2 Edition 1.0:2017, Hexavalent chromium – Determination of hexavalent chromium (Cr (VI) in polymers and electronics by the colorimetric method	10 mg/kg
Chromium (VI)(Cr ⁶⁺) Content	With reference to IEC 62321-7-1 edition 1.0:2015, by boiling water extraction and determined by UV- VIS spectrophotometer	0.10 µg/cm²
Polybrominated Biphenyls (PBBs)& Polybrominated Diphenyl Ethers (PBDEs)	With reference to IEC 62321-6 Edition 1.0: 2015, by solvent extraction and determined by GC/MS and further HPLC confirmation when necessary	5 mg/kg
Phthalates (DEHP, BBP, DBP, DIBP) Content	With reference to IEC 62321-8 Edition 1.0: 2017, by solvent extraction and determined by GC/MS	100 mg/kg


Intertek Testing Services Shenzhen Ltd. Guangzhou Branch Room 02, 1-8F.& Room 01,101/E201/E301/E401/E501/E601/E701/E801, No.7-2, Caipin Road, Science City, GETDD, Guangzhou, Guangdong, China. Tel: (86-20) 8213 9688 Fax: (86-20) 32057538 Website: <u>www.intertek.com</u>

Page 3 of 9



Report No.: 210719212GZU-003

- (D) Measurement Flowchart:
- 1. Test for Cd/Pb Contents






Report No.: 210719212GZU-003

Date: Aug 11, 2021

3. Test for Chromium (VI) (Cr6+) Content

Soluble polymers:




Intertek Testing Services Shenzhen Ltd. Guangzhou Branch Room 02, 1-8F.& Room 01,101/E201/E301/E401/E501/E601/E701/E801, No.7-2, Caipin Road, Science City, GETDD, Guangzhou, Guangdong, China. Tel: (86-20) 8213 9688 Fax: (86-20) 32057538 Website: www.intertek.com



Report No.: 210719212GZU-003

Date: Aug 11, 2021

4. Test for Chromium (VI) (Cr⁶⁺) Content (Boiling Water Extraction)








Test Report Report No.: 210719212GZU-003 Date: Aug 11, 2021 6. Test for Phthalate Contents Weigh sample and Extracted by Soxhlet Concentrate the place in a thimble extraction with extract organic solvent Make up with Transfer the extract Analyze by GC/MS organic solvent into a volumetric flask

Page 7 of 9



Report No.: 210719212GZU-003


Sample photo








Report No.: 210719212GZU-003





End of report

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.



Page 9 of 9